

Property	Standard	unit		Value
Grammage	ISO 536	g/m ²		80
Caliper	ISO 534	µm		104
Bulk	ISO 534	cm ³ /g		1.31
Breaking Length	ISO 1924-2	m	MD	6126
			CD	2879
Breaking Strength	ISO 1924-2	Kg/15mm	MD	7.3
			CD	3.4
Traction Index	ISO 1924-2	N-m/g	MD	60.1
			CD	28.2
Tear Index	ISO 1974	mN-m ² /g	MD	6.4
			CD	7.4
Burst	ISO 2758	kPa-m ² /g		2.2
Opacity	ISO2471	%		94
Bendtsen Smoothness	ISO 8791-2	ml/min		313/246
Bendtsen Porosity	ISO 5636-2	ml/min		1246
CIE Whiteness	ISO 11475	%		145.17

The indicated data corresponds to the typical values for this paper quality.