

Copystar

| Property | Standard | unit | | Value |
|---------------------|------------|-----------------------|----|---------|
| Grammage | ISO 536 | g/m ² | | 80 |
| Caliper | ISO 534 | µm | | 104 |
| Bulk | ISO 534 | cm ³ /g | | 1.31 |
| Breaking Length | ISO 1924-2 | m | MD | 6126 |
| | | | CD | 2879 |
| Breaking Strength | ISO 1924-2 | Kg/15mm | MD | 7.3 |
| | | | CD | 3.4 |
| Traction Index | ISO 1924-2 | N-m/g | MD | 60.1 |
| | | | CD | 28.2 |
| Tear Index | ISO 1974 | mN-m ² /g | MD | 6.4 |
| | | | CD | 7.4 |
| Burst | ISO 2758 | kPa-m ² /g | | 2.2 |
| Opacity | ISO2471 | % | | 94 |
| Bendtsen Smoothness | ISO 8791-2 | ml/min | | 313/246 |
| Bendtsen Porosity | ISO 5636-2 | ml/min | | 1246 |
| CIE Whiteness | ISO 11475 | % | | 145.17 |

The indicated data corresponds to the typical values for this paper quality.