

Kraft - Kraft

Uncoated two -sided KRAFT



Unprinted PIW



Printed PIW



Unprinted PIW

19.12.2025

TECHNICAL SPECIFICATIONS

Basis Weight		Stiffness Taber 15°				STIFFNESS L&W 5°	
g/m ² (a)	µm (b)	MD (gramf * cm) ©	CD (gramf * cm) ©	MD (mNm) ©	CD (mNm) ©	MD (mNm) ©	CD (mNm) ©
300	400	160	55	15.7	5.4	30.0	10.3
350	465	230	85	22.6	8.3	43.1	15.9
400	540	320	120	31.4	11.8	60.0	22.5
450	620	415	175	40.7	17.2	77.8	32.8
500**	690	505	240	49.5	23.5	94.6	45.0

** please check leadtime in advance

Humidity (%): 6-8		Recyclability EN 13430 Confirmed
Cobb Test 1 min: Top Side < 50		
Back Side < 50		
Bulk: 1.33 cm ³ / gr (d)		Biodegradability EN 13432 Confirmed
Delamination (ft*lb*10 ⁻³): MD >= 100 CD >= 100		
Gloss: 40-55		
*Tolerances:	a (±3%)	FSC 100% Recycled on request
	b (-5%)	
	c (-15%)	
	d (±5%)	

The product is suitable for dry foodstuff packaging

Storage conditions:

The product should be kept in a clean, shadowy place, free of odors and dust with relative humidity 50% (±3%)

The company reserves the right to change the technical specifications of its products