

ZICUBAG GR

Property	Standard	unit		Value	Value	Value	Value
Grammage	ISO 536	g/m ²		35 +/-2	40 +/-2	45 +/-2	50 +/-2
Caliper	ISO 534	µm		50 +/-2	55 +/-3	63 +/-3	70 +/-3
Bulk	ISO 534	cm ³ /g		1.45 +/-0.05	1.40 +/-0.05	1.40 +/-0.05	1.40 +/-0.05
Breaking Length	ISO 1924-2	m	MD	>7500	>7500	>7500	>7500
			CD	>3500	>3500	>3500	>3500
Traction Length	ISO 1924-2	N-m/g	MD	>73	>73	>73	>73
			CD	>34	>34	>34	>34
Tear Index	ISO 1974	mN-m ² /g	MD	>4.0	>4.5	>4.5	>5.0
			CD	>4.5	>5.0	>5.0	>5.5
Burst	ISO 2758	kPa-m ² /g		>4.5	>4.5	>4.5	>4.5
Cobb (60s)	ISO 535	g/m ²		<24	<24	<24	<24
Bendtsen Smoothness	ISO 8791-2	ml/min		<300	<300	<300	<300
Bendtsen Porosity	ISO 5636-2	ml/min		<1200	<1100	<1000	<1000
KIT Test	Tappi 559	n ^o		5 - 6	5 - 6	5 - 6	5 - 6

Conforms with Recommendation XXXVI of the German BfR Regulation for use in contact with Food

The indicated data corresponds to the typical values for this paper quality.