




**Kraft - Kraft (UT4)**

**Uncoated two -sided KRAFT**

-  Unprinted PIW
-  Printed PIW  
Mechanical Pulp
-  Unprinted PIW

**TECHNICAL SPECIFICATIONS**

Basis Weight g/m <sup>2</sup> (a)	µm (b)	StiffnessTaber 15°				STIFFNESS L&W 5°	
		MD (gramf * cm) ©	CD (gramf * cm) ©	MD (mNm) ©	CD (mNm) ©	MD (mNm) ©	CD (mNm) ©
300	400	160	55	15.7	5.4	30.0	10.3
350	465	230	85	22.6	8.3	43.1	15.9
400	540	320	120	31.4	11.8	60.0	22.5
450	620	415	175	40.7	17.2	77.8	32.8
500	690	505	240	49.5	23.5	94.6	45.0

<b>Humidity (%)</b> : 6-8		<b>Recycability</b> EN 13430 Confirmed
<b>Cobb Test 1 min</b> : Top Side < 50		
Back Side < 50		
<b>Bulk</b> : 1.33 cm <sup>3</sup> /gr (d)		<b>Biodegradability</b> EN 13432 Confirmed
<b>Delamination</b> (ft*lb*10 <sup>-3</sup> ): MD >= 100 CD >= 100		
<b>Gloss</b> : 40-55		
<b>*Tolerances:</b>	a (±3%)	
	b (-5%)	
	c (-15%)	
	d (±5%)	

The product is suitable for dry foodstuff packaging

**Storage conditions:**

The product should be kept in a clean, shadowy place, free of odors and dust with relative humidity 50% (±3%)

The company reserves the right to change the technical specifications of its products