



TRIPLEX R KRAFT

Fully Coated WLC with KRAFT back

 Multiple Pigment Coating

 Unprinted PIW

 Printed PIW
PCW

 Unprinted PIW

19.12.2025

TECHNICAL SPECIFICATIONS

Basis Weight g/m ² (a)	Thickness μm (b)	StiffnessTaber 15°				STIFFNESS L&W 5°	
		MD (gramf * cm) ©	CD (gramf * cm) ©	MD (mNm) ©	CD (mNm) ©	MD (mNm) ©	CD (mNm) ©
320	380	160	57	15.7	5.6	30.0	10.7
350	425	205	75	20.1	7.4	38.4	14.1
385**	470	274	101	26.9	9.9	51.3	18.9
400	485	297	111	29.1	10.9	55.7	20.8
450	555	393	154	38.5	15.1	73.6	28.9
500	620	489	192	48.0	18.8	91.6	36.0
550	700	565	227	55.4	22.3	105.9	42.5

** please check leadtime in advance

Humidity (%): 6-8%		Recyclability EN 13430 Confirmed
Brightness ISO(Elrepho)(%) : Top 80 ± 2		
Cobb Test 1 min: Top Side 35-65		
Bulk: 1.23 cm ³ /gr (d)		Biodegradability EN 13432 Confirmed
Delamination (ft*lb*10 ⁻³) : MD >= 50 CD >= 50		
Gloss: 40-55		
* Tolerances:	a (±3%)	FSC 100% Recycled on request
	b (-5%)	
	c (-15%)	
	d (±5%)	

The product is suitable for dry foodstuff packaging

Storage conditions:

The product should be kept in a clean, shadowy place, free of odors and dust with relative humidity 50% (±3%)

The company reserves the right to change the technical specifications of its products