

TRIPLEX BR

Fully Coated WLC
with coated reverse - White Back

 Multiple Pigment Coating

 Unprinted PIW

 Printed PIW
PCW

 Unprinted PIW

 Pigmentation

19.12.2025

TECHNICAL SPECIFICATIONS

Basis Weight g/m ² (a)	Thickness μm (b)	Stiffness Taber 15°				STIFFNESS L&W 5°	
		MD (gramf * cm) ©	CD (gramf * cm)	MD (mNm) ©	CD (mNm) ©	MD (mNm) ©	CD (mNm) ©
300	360	107	37	10.5	3.6	20.1	6.9
320	380	134	48	13.1	4.7	25.1	9.0
350	425	174	64	17.1	6.3	32.6	12.0
400	485	241	93	23.6	9.1	45.2	17.4
450	540	328	129	32.2	12.7	61.5	24.2
500	620	414	164	40.6	16.1	77.6	30.7
550	685	480	192	47.1	18.8	89.9	36.0
600	750	545	220	53.4	21.6	102.1	41.2

Humidity (%): 6-8%

Brightness ISO(Elrepho)(%) : Top 80 ± 2

Cobb Test 1 min: Top Side 35-65

Recyclability

EN 13430

Confirmed

Bulk: 1.23 cm³/gr (d)

Delamination (ft*lb*10⁻³): MD >= 50 CD >= 50

Gloss: 40-55

Biodegradability

EN 13432

Confirmed

*Tolerances:

a (±3%)

b (-5%)

c (-15%)

d (±5%)

FSC 100% Recycled

on request

The product is suitable for dry foodstuff packaging

Storage conditions: The product should be kept in a clean, shadowy place, free of odors and dust with relative humidity 50% (±3%)

The company reserves the right to change the technical specifications of its products