

EXCTS / GC2 code no. 12221


Technical specifications

Grammage	Caliper	Stiffness				
		L&W 5° md	L&W 5° cd	L&W 5° √(md x cd)	Taber 15° md	Taber 15° cd
g/m ²	µm	mNm	mNm		mNm	mNm
215	350	21.7	9.0	14.0	12.6	5.0
225	390	27.6	11.7	18.0	16.1	6.7
250	450	36.4	15.8	24.0	19.0	8.3
275	500	47.0	20.4	31.0	24.9	10.4
300	550	57.0	25.3	38.0	29.4	12.4
325	600	69.7	31.7	47.0	36.4	15.4
350	650	84.5	38.4	57.0	42.1	17.5

Tolerance and properties not related to grammage

Property	Value	Tolerances	Test standard
Brightness top (% Elrepho)	85	- 1	ISO 2470-2
Grammage (g/m ²)		+/- 2%	EN ISO 536
Caliper (µm)		+/- 5%, > 350 g/m ² +/- 3%	EN 20534
Stiffness (mNm)		- 15%	DIN 53121
Stiff. L&W cd. (mNm)		- 15%	DIN 53121
Geometric Mean L&W (mNm)			DIN 53121
Stiffness (mNm)		- 15%	TAPPI T489
Stiffn. taber cd. (mNm)		- 15%	TAPPI T489
Recyclability ()		in terms of the norm	EN 13430
Biodegradability ()		in terms of the norm	EN 13432

Board structure



Virgin fibre 90% of total board (+/-5%)

Pigment coating 10% of total board (+/-5%)

Certificates and statements

- ISO 9001
- ISO 22000 (incl. HACCP)
- ISO 50001
- FSC
- PEFC
- HALAL
- Vegan*
- Code of Conduct (CoC)
- EURT - Timber Regulation No. 9952010 - (Declaration of origin)
- Food Safety Statement*
- Law and Regulations Statement*
- Chemical Statement*
- Migration Statement (MOSH/MOAH)

* Check our website for all details about our certificates and statements

More information about our products, including our certificates, are available on www.folbb.com

¹Permissible: -15% of the target stiffness. This applies to 100% of all measured single values. The single value is a calculated average of five measurements per sheet. The stiffness has to be measured at both sides. The resulting average value is then the stiffness of the single sample. L&W 5° figures are binding, Taber figures are indicative. All figures mentioned above may be subject to technical changes.

EXCTS / GC2 code no. 12221



Features

- stiff and high yield
- excellent runnability for outstanding production efficiency
- conformity for direct food contact applications

Applications

- Dry Food
- Chilled Food (secondary packaging)
- Frozen Food
- Chocolate and Confectionery
- Food Service
- Pharma and Health Care
- Cosmetics and Personal Care

Mill Information

- benchmark for service and constant quality
- specialised in cartonboard qualities for challenging applications
- experienced, innovative production team and professional technical support
- strategically located to the Western and Eastern European markets
- short transportation routes and flexible service guaranteed

Excellent Top Strong is light-weight with strong properties: Excellent Top Strong combines excellent stiffness with maximum converting efficiency, while maintaining the consistently high quality customers have come to expect and offering premium service from the German virgin fibre mill in Baiersbronn.

If you are interested in EXCELLENT TOP STRONG or have any further questions, please contact sales.baiersbronn@folbb.com

www.folbb.com

[General Terms of Trade](#)

It is a general recommendation for enduse applications; legally binding is only the declaration of compliance issued by FOLBB for each individual type of cartonboard.