

ZICUFLEX

Property	Standard	unit		Value	Value	Value	Value
Grammage	ISO 536	g/m ²		35 +/-2	40 +/-2	45 +/-2	50 +/-2
Caliper	ISO 534	µm		39 +/-2	44 +/-2	50 +/-2	55 +/-3
Bulk	ISO 534	cm ³ /g		1.10 +/-0.05	1.10 +/-0.05	1.10 +/-0.05	1.10 +/-0.05
Breaking Length	ISO 1924-2	m	MD	>6500	>6500	>6500	>6500
			CD	>3000	>3000	>3000	>3000
Traction Length	ISO 1924-2	N-m/g	MD	>63	>63	>63	>63
			CD	>29	>29	>29	>29
Tear Index	ISO 1974	mN-m ² /g	MD	>2.8	>2.8	>2.8	>2.8
			CD	>4.2	>4.2	>4.2	>4.2
Burst	ISO 2758	kPa-m ² /g		>4.5	>4.5	>4.5	>4.5
Cobb (60s)	ISO 535	g/m ²		<28	<28	<28	<28
Bekk Smoothness	ISO 5627	s		>90	>90	>90	>90
Bendtsen Porosity	ISO 5636-2	ml/min		<1100	<1100	<1100	<1100
CIE Whiteness	ISO 11475	%		>140	>140	>140	>140

Conforms with Recommendation XXXVI of the German BfR Regulation for use in contact with Food

The indicated data corresponds to the typical values for this paper quality.

*: Also available without optical brightener.