

## Zicuset

Property	Standard	unit		Value	Value	Value	Value
Grammage	ISO 536	g/m <sup>2</sup>		60	70	80	90
Caliper	ISO 534	µm		74	85	97	117
Bulk	ISO 534	cm <sup>3</sup> /g		1.23	1.22	1.21	1.3
Breaking Length	ISO 1924-2	m	MD	7055	7833	7288	6516
			CD	3517	3415	3188	3072
Breaking Strength	ISO 1924-2	Kg/15mm	MD	6.3	8.3	8.8	8.8
			CD	3.2	3.6	3.8	4.2
Traction Index	ISO 1924-2	N-m/g	MD	69.2	76.8	71.5	63.9
			CD	34.5	33.5	31.3	30.1
Tear Index	ISO 1974	mN-m <sup>2</sup> /g	MD	6.1	6.5	6.6	6.7
			CD	7.0	7.5	7.9	7.6
Burst	ISO 2758	kPa-m <sup>2</sup> /g		2.4	2.3	2.4	2.7
Opacity	ISO2471	%		86.89	91.9	94.39	95.85
Bendtsen Smoothness	ISO 8791-2	ml/min		102/180	239/163	258/181	293/217
Bendtsen Porosity	ISO 5636-2	ml/min		772	736	770	838
CIE Whiteness	ISO 11475	%		143.07	146.83	147.59	147.02

The indicated data corresponds to the typical values for this paper quality.