



PAPELERA GUIPUZCOANA DE ZICUÑAGA, S. A.

ZCopy office paper

Property	Standard	unit		Value	
Grammage	ISO 536	g/m ²		75	
Caliper	ISO 534	μm		100	
Bulk	ISO 534	cm ³ /g		1.33	
Breaking Length	ISO 1924-2	m	MD	6378	
			CD	3080	
Breaking Strength	ISO 1924-2	Kg/15mm	MD	7.2	
			CD	3.5	
Traction Index	ISO 1924-2	N-m/g	MD	62.6	
			CD	30.2	
Tear Index	ISO 1974	mN-m ² /g	MD	6.5	
			CD	7.6	
Burst	ISO 2758	kPa-m ² /g		2.3	
Opacity	ISO2471	%		93.73	
Bendtsen Smoothness	ISO 8791-2	ml/min		308/238	
Bendtsen Porosity	ISO 5636-2	ml/min		1292	
CIE Whiteness	ISO 11475	%		149.78	

The indicated data corresponds to the typical values for this paper quality.