

## AC (PH 0.3) / GC2 code no. 12207


### Technical specifications

Grammage	Caliper	Stiffness				
		L&W 5° md mNm	L&W 5° cd mNm	L&W 5° v(md x cd)	Taber 15° md mNm	Taber 15° cd mNm
g/m <sup>2</sup>	µm					
200	310	11.7	5.8	8.2	5.9	2.7
215	340	15.0	7.6	10.7	7.7	3.6
230	370	18.4	9.5	13.2	9.8	4.9
245	400	22.0	11.5	15.9	11.9	6.0
265	440	28.5	14.3	20.2	15.0	7.6
275	460	32.0	15.8	22.5	16.7	8.5
290	490	37.0	18.6	26.2	19.7	10.0
305	520	41.6	21.4	29.8	22.7	11.6
325	560	49.0	25.2	35.1	27.4	14.1
350	615	60.0	31.5	43.5	34.1	17.6
375	670	73.0	39.0	53.4	41.9	21.6
400	725	88.2	46.7	64.2	50.8	26.3
425	780	105.5	55.7	76.7	60.8	31.4
450	840	125.0	65.1	90.2	71.8	37.1

### Tolerance and properties not related to grammage

Property	Value	Tolerances	Test standard
Brightness top (% Elrepho)	90	- 1	ISO 2470-2
Grammage (g/m <sup>2</sup> )		+/- 2%	EN ISO 536
Caliper (µm)		+/- 5%, > 350 g/m <sup>2</sup> +/- 3%	EN 20534
Stiffness (mNm)		- 15%	DIN 53121
Stiff. L&W cd. (mNm)		- 15%	DIN 53121
Geometric Mean L&W (mNm)			DIN 53121
Stiffness (mNm)		- 15%	TAPPI T489
Stiffn. taber cd. (mNm)		- 15%	TAPPI T489
Recyclability		in terms of the norm	EN 13430
Biodegradability		in terms of the norm	EN 13432

### Board structure



Virgin fibre 90% of total board (+/-5%)

Pigment coating 10% of total board (+/-5%)

<sup>1</sup>Permissible: -15% of the target stiffness. This applies to 100% of all measured single values. The single value is a calculated average of five measurements per sheet. The stiffness has to be measured at both sides. The resulting average value is then the stiffness of the single sample. L&W 5° figures are binding, Taber figures are indicative. All figures mentioned above may be subject to technical changes.

AC (PH 0.3) / GC2 code no. 12207



Accurate (PH 0.3) has optimum laser and inkjet coding properties and is subject to increased quality controls. Recommended quality for pharma packaging, which have a 2D matrix code as a unique identifier. With the Directive 2011/62/EU (Falsified Medicines Directive) 2D matrix codes are mandatory on each primary and secondary packaging of medicinal products since 1Q 2019.

If you are interested in ACCURATE or have any further questions, please contact [sales.eerbeek@folbb.com](mailto:sales.eerbeek@folbb.com)

[www.folbb.com](http://www.folbb.com)

[General Terms of Trade](#)

This is a general recommendation. The cardboard should be checked for suitability before use.

## Features

- optimum laser and inkjet coding properties
- increased quality controls
- ideal results for Braille embossing
- impressive brightness
- attractive bright reverse side
- high smoothness
- brilliant gloss levels

## Applications

- Pharma and Health Care

## Mill Information

- comprehensive portfolio of virgin fibre cartonboard
- including qualities with special barriers against moisture and grease
- experienced, innovative production team and professional technical support
- strategically located to the Western, Eastern and Northern European markets
- flexible leadtimes and excellent service guaranteed

## Certificates and statements

- ISO 9001
- ISO 14001
- ISO 22000 (incl. HACCP)
- ISO 50001
- FSC® (FSC® C170805)\*
- PEFC (PEFC/04-31-3649)\*
- HALAL
- Code of Conduct (CoC)
- EUTR - Timber Regulation No. 9952010 - (Declaration of origin)
- Food Safety Statement
- Law and Regulations Statement
- Chemical Statement
- Migration Statement (MOSH/MOAH)

Our products are also available with FSC® or PEFC certification on request.

**More information about our products, including our certificates, are available on [www.folbb.com](http://www.folbb.com)**