








TRIPLEX BR (GT2)

Fully Coated WLC
with coated reverse - White Back

-  Multiple Pigment Coating
-  Unprinted PIW
-  Printed PIW
-  Mechanical Pulp
-  PCW
-  Unprinted PIW
-  Pigmentation

TECHNICAL SPECIFICATIONS

Basis Weight g/m ² (a)	Thickness µm (b)	Stiffness Taber 15°				STIFFNESS L&W 5°	
		MD (gramf * cm) ©	CD (gramf * cm)	MD (mNm) ©	CD (mNm) ©	MD (mNm) ©	CD (mNm) ©
300	360	107	37	10.5	3.6	20.1	6.9
320	380	134	48	13.1	4.7	25.1	9.0
350	425	174	64	17.1	6.3	32.6	12.0
400	485	241	93	23.6	9.1	45.2	17.4
450	540	328	129	32.2	12.7	61.5	24.2
500	620	414	164	40.6	16.1	77.6	30.7
550	685	480	192	47.1	18.8	89.9	36.0
600	750	545	220	53.4	21.6	102.1	41.2

Humidity (%) : 6-8%		Recycability EN 13430 Confirmed
Brightness ISO(Elepho)(%) : Top 80 ± 2		
Cobb Test 1 min : Top Side 35-65		
Bulk : 1.23 cm ³ /gr (d)		Biodegradability EN 13432 Confirmed
Delamination (ft*lb*10⁻³) : MD >= 50 CD >= 50		
Gloss : 40-55		
*Tolerances:	a (±3%)	
	b (-5%)	
	c (-15%)	
	d (±5%)	

The product is suitable for dry foodstuff packaging

Storage conditions: The product should be kept in a clean, shadowy place, free of odors and dust with relative humidity 50% (±3%)