







TRIPLEX RKR (GT4)

Fully Coated WLC with KRAFT back

-  Multiple Pigment Coating
-  Unprinted PIW
-  Printed PIW
-  Mechanical Pulp
-  PCW
-  Unprinted PIW

TECHNICAL SPECIFICATIONS

Basis Weight g/m <sup>2</sup> (a)	Thickness µm (b)	Stiffness Taber 15°				STIFFNESS L&W 5°	
		MD (gramf * cm) ©	CD (gramf * cm) ©	MD (mNm) ©	CD (mNm) ©	MD (mNm) ©	CD (mNm) ©
320	380	160	57	15.7	5.6	30.0	10.7
350	425	205	75	20.1	7.4	38.4	14.1
385	470	274	101	26.9	9.9	51.3	18.9
400	485	297	111	29.1	10.9	55.7	20.8
450	555	393	154	38.5	15.1	73.6	28.9
500	620	489	192	48.0	18.8	91.6	36.0
550	700	565	227	55.4	22.3	105.9	42.5

<b>Humidity (%)</b> : 6-8%		<b>Recycability</b> EN 13430 Confirmed
<b>Brightness ISO(Elrepho)(%)</b> : Top 80 ± 2		
<b>Cobb Test 1 min</b> : Top Side 35-65		
<b>Bulk</b> : 1.23 cm <sup>3</sup> /gr (d)		
<b>Delamination</b> (ft*lb*10 <sup>-3</sup> ): MD >= 50 CD >= 50		<b>Biodegradability</b> EN 13432 Confirmed
<b>Gloss</b> : 40-55		
<b>* Tolerances:</b>	a (±3%)	
	b (-5%)	
	c (-15%)	
	d (±5%)	

The product is suitable for dry foodstuff packaging

**Storage conditions:**

The product should be kept in a clean, shadowy place, free of odors and dust with relative humidity 50% (±3%)

The company reserves the right to change the technical specifications of its products